

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 July 2004 (15.07.2004)

PCT

(10) International Publication Number
WO 2004/058877 A1

(51) International Patent Classification⁷: **C08L 23/04**,
C08F 297/08

Hopfenstrasse 6, 65520 Bad Camberg (DE). MANTEL,
Rainer [DE/DE]; Augustaanlage 26, 68165 Mannheim
(DE).

(21) International Application Number:
PCT/EP2003/013974

(22) International Filing Date:
10 December 2003 (10.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
102 61 064.9 24 December 2002 (24.12.2002) DE
60/445,165 5 February 2003 (05.02.2003) US

(71) Applicant (for all designated States except US): **BASELL
POLYOLEFINE GMBH** [DE/DE]; Brühler Strasse,
50389 Wesseling (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BERTHOLD**,
Joachim [DE/DE]; Am Flachsland 54, 65779 Kelkheim
(DE). **BÖHM**, Ludwig [DE/DE]; Leonhardstrasse 36,
65795 Hattersheim (DE). **KRÜMPEL**, Peter [DE/DE];

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR,
CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD,
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,
SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: POLYETHYLENE COMPOSITION FOR PRODUCING L-RING DRUMS

(57) Abstract: The invention relates to a polyethylene composition with multimodal molecular mass distribution, which is partic-
ularly suitable for the blow molding of L-ring drums having a volume in the range of from 50 to 250 dm³ (l). The composition has
a density in the range of from 0.950 to 0.956 g/cm³ at 23 °C and a MFR_{1g/21.6} in the range from 1.5 to 3.5 dg/min. It comprises
from 35 to 45 % by weight of a low-molecular-mass ethylene homopolymer A, from 34 to 44 % by weight of a high-molecular-mass
copolymer B made from ethylene and from another 1-olefin having from 4 to 8 carbon atoms, and from 18 to 26 % by weight of an
ultrahigh-molecular-mass ethylene copolymer C.

WO 2004/058877 A1